

CowMotion

Hoof Glue

Technical data sheet

ACRYLATE ADHESIVE
Two-component



CowMotion Hoof Glue MULTI CRAFT BLACK

CowMotion Hoof Glue Multi Craft enables high-strength, structural and at the same time flexible, durable adhesive joints.

CowMotion Hoof Glue Multi Craft is an industrial adhesive used to join metals, plastics and composites. Due to its high quality, it is specially tailored to the requirements of a wide range of industrial applications. Use of primers is not necessary for bonding aluminum and stainless steel. Due to its flexibility also materials with different coefficients of thermal expansion can be structurally bonded. Compared to conventional MMA adhesives, CowMotion Hoof Glue Multi Craft scores with extremely low shrinkage as well as thermal, chemical and climatic stability.

With two container sizes, integrated into an optimal system of cartridge, dispensing gun and mixer, we offer a comprehensive, individual solution.

Sizes / article number

50ml cartridge

Storage & Durability

The shelf life is, at the optimum storage temperature of +2 °C to +23 °C in the closed original container, a maximum of 9 months. A higher storage temperature leads to a significantly lower durability and can lead to damage of the cartridge. The storage temperature must not be lower than +2 °C.

Properties (single components)

	Adhesive	Activator
Colour:	grey	black
Viscosity ¹⁾ [mPas]:	100.000-140.000	80.000-120.000
Mixing ratio A:B (volume):		10 : 1
Mixing ratio A:B (weight):		9 : 1
Density ²⁾ [g/ml]:	0,96 - 1,02	1,05 - 1,15
Flashpoint ³⁾ [°C]:		+12
Gap filling [mm]:		1 - 15

1) At 25 °C, Brookfield viscometer

2) Measured according to DIN 53217, part 2 density sphere model 475 / III

3) Measured according to DIN 51755



Properties (cured adhesive)

Colour:	black
Processing time [min]:	1 - 2
Fixing time [min]:	2 - 3,5
Final strength after [h]:	24
Density ¹⁾ [g/ml]:	0.96 to 1.02
Temperature resistance [°C]:	-40 to +100
Elongation at break ²⁾ [%]:	approx. 70

1) Theoretical calculation from the densities of the individual components

2) Measured according to ASTM D638 / DIN ISO 6892

Tensile shear strengths¹⁾

Substrates	Tensile shear strengths [N/mm ²]
PVC	16 - 20
ABS	13 - 17
Cold rolled steel	13 - 17
Aluminum	17 - 21
Stainless steel	13 - 17
Acrylate	20 - 24

1) Tested to GLUETEC AA-029

Adhesion spectrum

Metals	Plastics	Composite materials
Aluminum ✓	Acrylates ✓	Vinyl ✓
Stainless steel ✓	Styrenics ✓	Carbon fibre ✓
Structural steel ✓	ABS Plastic ✓	Polyester (DCPD mod.) ✓
Powder coated metals ✓	PVC/CPVC ✓	Urethanes ✓
Galvanized metals ✗	Polyethylenes ✗	GRP/FRP ✓
	Polypropylenes ✗	Epoxy5 ✓
	Polytetrafluorethylenes (PTFE) ✗	Gelcoats6 ✓
	Polyacetals ✗	

Instructions

Application

The optimum processing temperature is between +18 °C and +25 °C. A higher or lower temperature affects the processing time. Before each use it must be ensured that the mixer to be used is correctly attached to the cartridge and that the cartridge is correctly placed in the dispensing gun. Furthermore, it must be ensured that the surfaces to be bonded are not contaminated with oils, dust, paint, oxidation layers and all other contaminants. Before applying to the surfaces to be bonded, it is essential to squeeze a small amount of the adhesive to ensure complete mixing of both components, otherwise the adhesion properties will be reduced. The subsequent joining of the materials must take place within the processing time. After the end of the processing time, no strong mechanical stress on the adhesive should be achieved until complete curing, otherwise the adhesion properties will be affected. If you have further questions about the product or its application, please contact our application engineering.



Surface preparation

In order to guarantee the optimum properties of CowMotion Multi Craft, it is imperative to clean the surfaces. The cleaning measures are to be individually adjusted to the materials and surfaces to be bonded:

Metals:

1. Use a clean cloth and pure acetone or isopropanol to remove dust and dirt from the surface.
2. Lightly roughen the surface by sanding or blasting.
3. Repeat step 1.

Plastics / Composites:

1. Clean the surface with a clean cloth and isopropyl alcohol to remove dust and dirt.
2. Lightly roughen the surface by grinding.
3. Repeat step 1.

CAUTION: Do not use gasoline or low quality alcohol for pretreatment.

Note:

Please note the information and notes in our respective safety data sheets. The data contained herein are for informational purposes only and are believed to be accurate to the best of our knowledge. We assume no liability for the results. For optimum functionality of the adhesive system, please only use the cartridge and mixer systems tested and released by GLUETEC. The product is only suitable for professional and experienced users. It is the user's own responsibility to take precautions to protect property and people from the hazards that may be encountered in handling and using these products. Accordingly, GLUETEC specifically disclaims any warranty, expressed or implied, including any warranty or suitability commitments for a particular purpose. In particular, GLUETEC disclaims all liability for consequential or indirect damages of any kind.

